

Verpackungstahlbänder

Abmessung mm	Oberfläche	Bruchdehnung A5 (%) ca.	Zugfestigkeit N/mm ²	Gesamtbelastung N ca.	Lieferform	Meter je 100 kg
Blankband						
12,7 x 0,40	blank	3	750	3800	S	2508
12,7 x 0,50	blank	3	750	4750	S	2006
16,0 x 0,40	blank	3	750	4800	S	1990
16,0 x 0,50	blank	3	750	6000	S	1592
16,0 x 0,60	blank	3	750	7200	S	1326
19,0 x 0,50	blank	3	750	7100	S	1340
19,0 x 0,60	blank	3	750	8500	S	1064
19,0 x 0,80	blank	4	680	10350	S	838
24,4 x 0,80	blank	4	680	13800	S	626
24,4 x 1,00	blank	5	680	17250	S	501
31,75 x 0,80	blank	5	680	17250	S	501
31,75 x 1,00	blank	5	680	21500	S	401

VG Spezial vergütet, gebläut oder lackiert

12,7 x 0,40	B/S/Z	6	850	4300	P/S	2508
12,7 x 0,50	B/S/Z	6	850	5400	P/S	2006
16,0 x 0,40	B/S/Z	6	850	5450	P/S	1990
16,0 x 0,50	B/S/Z	6	850	6800	P/S	1592
16,0 x 0,60	B/S/Z	6	850	8150	P/S	1326
19,0 x 0,50	B/S/Z	6	850	8100	P/S	1340
19,0 x 0,60	B/S/Z	8	850	9700	P/S	1064
19,0 x 0,80	B/S/Z	8	750	11400	P/S	838
24,4 x 0,80	B/S/Z	8	750	15200	S	626
24,4 x 1,00	B/S/Z	8	750	19000	S	501
31,75 x 0,80	B/S/Z	8	750	19000	S	501
31,75 x 1,00	B/S/Z	8	750	22000	S	401

HL Hochleistungsband, gebläut oder lackiert

12,7 x 0,50	B/S/Z	15	950	6350	P	2006
16,0 x 0,50	B/S/Z	15	950	7940	P	1592
16,0 x 0,60	B/S/Z	15	950	9350	P	1326
19,0 x 0,60	B/S/Z	15	950	11400	P	1064
19,0 x 0,80	B/S/Z	15	950	14450	P	838
24,4 x 0,80	B/S/Z	15	950	19300	S	626
31,75 x 0,80	B/S/Z	15	950	24250	S	501

Oberfläche: B = gebläut
 S = schwarzlackiert
 Z = zink lackiert

Lieferform: S = Scheibenwicklung
 P = Packenwicklung